



PRODUCT INFORMATION DATA SHEET

17451 Von Karman Avenue, Irvine, CA 92614
Tel (949) 474-0400 (800) 544-3338
Fax (949) 474-7269
www.deftfinishes.com

02GN084 (02-GN-84)

Non-Chrome Epoxy

Polyamide Primer

Product Information

Specifications	MIL-PRF-23377K Type I Class N 5PTMRA01
Description	Chemically cured, non-chromate, two-component epoxy polyamide primer
Features	<ul style="list-style-type: none">Corrosion inhibitingChemical and Solvent ResistantResistant to immersion in Hydraulic Fluids, Lubricating Oils, Phosphate Ester Based Hydraulic Fluids, Skydrol and Distilled water
Color	Aqua Green
Reducer	None required. May be reduced with IS-237*
Mix Ratio	3 parts 02GN084 base by volume to 1 part 02GN084CAT catalyst by volume

Kit size	02GN084 base	02GN084CAT
GK	96 oz / 2.84 L	32 oz / 946 mL
QK	24 oz / 710 mL	8 oz / 237 mL

Pot Life	4 hours at 75° ± 10°F
Viscosity	initial: 20 ± 2 seconds # 2 EZ Zahn Cup 40 seconds, max, # 4 Ford Cup Pot life: 70 seconds, max, # 4 Ford Cup
Induction Time	None required**
Application Thickness	0.6 – 0.9 mils dry film thickness
Storage Stability	2 years from DOM when stored between 72 - 80°F
Recommended Storage	Store indoors between 70 – 90°F in original unopened containers.

*Use only if needed and if local and state VOC limits allow.
**30 minutes required per TO 1-1-8, 6.12.2.3 [JAN 12, 2010]

Characteristics*

Characteristics	Base	Catalyst	Admixed
Weight per gallon (lbs)	11.8	8.9	11.06
% Solids by weight	51.1	82.2	57.4
% Solids by volume	39.2	76.5	48.5
Coatings VOC (g/L)	405	190	338
Coatings VOC (lbs/gal)	3.4	1.6	2.8
Material VOC (g/L)	297	190	270
Material VOC (lbs/gal)	2.5	1.6	2.3

Dry film density**: 1.57 g/cc
Theoretical Coverage** per gallon as applied: 778 sq. ft.
Theoretical Dry Film Weight per gallon kit as applied:
3.70 g/sq. ft (0.00815-lbs/sq. ft)

* Characteristics are calculated based on product formulas and ingredient characteristics as reported to Deft, Incorporated by raw material suppliers. Values reported are not specification values. They are presented for general information only.
** Dry film density and theoretical coverage based on proper application of coating at 1 mil dry film thickness and 100% transfer efficiency.

Dry Times

Topcoat Window: 5 – 24 hours* **Tack Free:** 2 hours, min
Dry Hard: 8 hours, max **Full Cure:** 14 days, max

*Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% Relative Humidity. After 24 hours of cure, scuff sand the entire primed surface followed by solvent wiping prior to top coating. [Ref: T.O. 1-1-8 Section 6.12.2.5, JAN 12, 2010]

Forced Dry Schedule

For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
120°F	45 minutes
140°F	30 minutes
160°F	20 minutes
180°F	15 minutes

* Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% Relative Humidity.

Mixing and Thinning

GK & QK: Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not stir or shake the base component longer than 5 minutes. Slowly add the one volume of catalyst to three volumes base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. DO NOT SHAKE OR MECHANICALLY MIX MATERIAL FOR LONGER THAN 10 MINUTES. Constant agitation of the material during spray application is recommended.

Application Equipment

Conventional, Air, Air Assisted Airless, HVLP, Electrostatic spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional, HVLP or Electrostatic spray applications, and recommendations on hose diameter and lengths.

Packaging, Yields, Shipping Weight

This material is available in the follow kit sizes:

Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight
GK	1 gallon (3.8 L)	12.3 lbs (5.6 kg)
QK	1 quart (946 mL)	3.6 lbs (1.6 kg)

Additional kit sizes are available upon request.

Equipment Cleanup

Use IS-237 Epoxy Reducer (MIL-T-81772B Type II) to remove any liquid or residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment

Safety

Refer to the product label or Material Safety Data Sheet (MSDS) for each component for Personal Protective Equipment and Proper Handling.