



PRODUCT INFORMATION DATA SHEET

17451 Von Karman Avenue, Irvine, CA 92614
Tel (949) 474-0400 (800) 544-3338
Fax (949) 474-7269
www.deftfinishes.com

02Y040A (02-Y-40A)

MIL-PRF-23377K TY I CL C2

Epoxy Polyamide Primer

Product Information			Forced Dry Schedule												
Specifications	MIL-PRF-23377K Type I Class C2		<p>For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.</p> <table><tr><th>Temperature</th><th>Time</th></tr><tr><td>120°F</td><td>45 minutes</td></tr><tr><td>140°F</td><td>30 minutes</td></tr><tr><td>160°F</td><td>20 minutes</td></tr><tr><td>180°F</td><td>15 minutes</td></tr></table> <p>* Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% Relative Humidity.</p>			Temperature	Time	120°F	45 minutes	140°F	30 minutes	160°F	20 minutes	180°F	15 minutes
Temperature	Time														
120°F	45 minutes														
140°F	30 minutes														
160°F	20 minutes														
180°F	15 minutes														
Description	Chemically cured, strontium chromate, two-component epoxy polyamide primer														
Features	<ul style="list-style-type: none">Corrosion inhibitingChemical and Solvent ResistantResistant to Hydraulic Fluids, Lubricating Oils, Phosphate Ester Based Hydraulic Fluids, Skydrol and Distilled water														
Color	Yellow														
Reducer	None required. May be reduced with IS-237*														
Mix Ratio	3 parts 02Y040A base by volume to 1 part 02Y040ACAT catalyst by volume														
Kit size	02Y040A base	02Y040ACAT	Mixing and Thinning												
GK	1 can filled @ 96 oz / 2.84 L	1 can filled @ 32 oz / 946 mL													
3QK	2 cans filled @ 24 oz / 710 mL	2 cans filled @ 8 oz / 237 mL													
Pot Life	4 hours at 75° ± 10°F		<p>GK & 3QK: Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not stir or shake the base component longer than 5 minutes. Slowly add the one volume of catalyst to three volumes base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. DO NOT SHAKE OR MECHANICALLY MIX MATERIAL FOR LONGER THAN 10 MINUTES. Constant agitation of the material during spray application is recommended.</p>												
Viscosity	initial: 40 seconds, max, # 4 Ford Cup Pot life: 70 seconds, max, # 4 Ford Cup														
Induction Time	None required														
Application Thickness	0.6 – 0.9 mils dry film thickness														
Storage Stability	1 year from DOM when stored between 35 - 115°F														
Recommended Storage	Store indoors between 70 – 90°F in original unopened containers.														
*Use only if needed and if local and state VOC limits allow.			Application Equipment												
Characteristics*															
Characteristics	Base	Catalyst	Admixed	<p>Conventional, Air, Air Assisted Airless, HVLP, Electrostatic spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional, HVLP or Electrostatic spray applications, and recommendations on hose diameter and lengths.</p> <p>Packaging, Yields, Shipping Weight</p> <p>This material is available in the follow kit sizes:</p> <table><tr><th>Kit size</th><th>Approx. Yield (Mixed)</th><th>Approx. Shipping Weight</th></tr><tr><td>GK</td><td>1 gallon (3.8 L)</td><td>13 lbs (5.9kg)</td></tr><tr><td>3QK</td><td>2 quarts (1.9 L)</td><td>6.6 lb (3.0 kg)</td></tr></table> <p>Additional kit sizes are available upon request.</p> <p>Equipment Cleanup</p> <p>Use IS-237 Epoxy Reducer (MIL-T-81772B Type II) to remove any liquid or residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment</p>			Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight	GK	1 gallon (3.8 L)	13 lbs (5.9kg)	3QK	2 quarts (1.9 L)	6.6 lb (3.0 kg)
Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight													
GK	1 gallon (3.8 L)	13 lbs (5.9kg)													
3QK	2 quarts (1.9 L)	6.6 lb (3.0 kg)													
Weight per gallon (lbs)	13.0	8.0	11.75												
% Solids by weight	74.0%	73.2	71.8%												
% Solids by volume	56.0%	69.5	59.4%												
Coatings VOC (g/L)	315	372	330												
Coatings VOC (lbs/gal)	2.6	3.1	2.8												
Material VOC (g/L)	287	372	308												
Material VOC (lbs/gal)	2.4	3.1	2.6												
Dry film density**: 1.70 g/cc			Safety												
Theoretical Coverage** per gallon as applied: 953 sq. ft.															
Theoretical Dry Film Weight per gallon kit as applied: 4.0g/sq. ft (0.00881-lbs/sq. ft)															
* Characteristics are calculated based on product formulas and ingredient characteristics as reported to Deft, Incorporated by raw material suppliers. Values reported are not specification values. They are presented for general information only.			Refer to the product label or Material Safety Data Sheet (MSDS) for personal protective equipment and proper handling.												
** Dry film density and theoretical coverage based on proper application of coating at 1 mil dry film thickness and 100% transfer efficiency.															
Dry Times															
Dry to Topcoat: 5 hours, min-24 hours max Tack Free: 5 hours, max															
Dry Hard: 8 hours, max Full Cure: 14 days, max															
*Note: Dry times are based on film thickness. Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% Relative Humidity. After 8 hours of cure, solvent wipe the entire primed surface with IS- 297 Primer Re-activator, Acetone or equivalent. After 24 hours of cure, scuff sand the entire primed surface, followed by a solvent wipe.															