



## PRODUCT INFORMATION DATA SHEET

17451 Von Karman Avenue, Irvine, CA 92614  
Tel (949) 474-0400 (800) 544-3338  
Fax (949) 474-7269  
www.deftfinishes.com

44GN007 (44-GN-7)

Water Reducible

Epoxy Primer

### Product Information

**Qualified Specifications** **MIL-PRF-85582E TYPE I CLASS C1 STW4-9143 REV B SCN 3**

**Description** Chromated, water reducible, chemically cured, two-component epoxy polyamide primer

**Features**

- Corrosion inhibiting
- Chemical and Solvent Resistant
- Resistant to Hydraulic Fluids, Lubricating Oils, Phosphate Ester Based Hydraulic Fluids and Distilled water

**Color** Green

**Reducer** Distilled or Deionized water (200% reduction)

**Mix Ratio** 3 parts 44GN007 base by volume to 1 part 44GN007CAT catalyst by volume to 8 parts water by volume (200% reduction)

Kit size	44GN007base	44GN007CAT	D.I. Water
GK	96 oz / 2.84 L	32 oz / 946 mL	256 oz / 7.57 L
QK	24 oz / 710ml	8 oz / 237ml	64 oz / 1.89 L
1QK	8 oz / 237ml	2.7oz / 80ml	21oz / 621ml

**Pot Life** 4 hours at 73° ± 5°F

**Viscosity** initial: 20 ± 2 seconds # 2 EZ Zahn Cup  
16 ± 2 seconds # 4 Ford Cup  
Pot life: ≤ 8-second rise (typical)

**Induction Time** none required

**Application Thickness** 0.6 – 0.9 mils dry film thickness

**Storage Stability (Per MIL-PRF-85582)** 1 year when stored between 35 – 115°F

**Recommended Storage** Store indoors between 70 – 90°F in original unopened containers.

### Characteristics (At 200% Reduction)\*

Characteristics	Base	Catalyst	Admixed
Weight per gallon (lbs)	12.69	9.52	9.52
% Solids by weight	74.4%	83.7%	31.8%
% Solids by volume	55.9%	82.3%	20.8%
Coatings VOC (g/L)	390	186	339
Coatings VOC (lbs/gal)	3.25	1.55	2.82
Material VOC (g/L)	390	186	113
Material VOC (lbs/gal)	3.25	1.55	0.94

**Dry film density\*\*:** 1.66 g/cc

**Theoretical Coverage\*\* per gallon as applied:** 334 sq. ft.

**Theoretical Coverage per gallon kit as applied:** 1002 sq. ft.

**Theoretical Dry Film Weight per gallon kit as applied:** 4.10 g/sq. ft (0.00904-lbs/sq. ft)

\* Characteristics are calculated based on product formulas and ingredient characteristics as reported to Deft, Incorporated by raw material suppliers. Values reported are not specification values. They are presented for general information only.

\*\* Dry film density and theoretical coverage based on proper application of coating at 1 mil dry film thickness and 100% transfer efficiency.

### Dry Times

**Tack Free** 1 hours, min      **Dry to Tape** 6 hours, min

**Dry Hard** 6 hours, max

Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% Relative Humidity.

### Forced Dry Schedule

For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures\* prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

Temperature	Time
120°F	45 minutes
140°F	30 minutes
160°F	20 minutes
180°F	15 minutes

\* Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% Relative Humidity.

### Mixing and Thinning

**GK & QK:** Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not stir or shake the base component longer than 5 minutes. Slowly add the one volume of catalyst to three volumes base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. **DO NOT SHAKE OR MECHANICALLY MIX MATERIAL FOR LONGER THAN 10 MINUTES.** To the catalyzed primer, add approx. 8 volumes (200%) of distilled or deionized water. Slowly add the water in one-third increments, mixing thoroughly after each addition, until fully incorporated and homogeneous. Be sure to scrape the sides and bottom of the container. Constant agitation of the material during spray application is recommended. The water is used to adjust the viscosity. Volumes of water needed may vary between 175 – 225%. **1QK:** Add the entire catalyst component to the base component. Fill the can to the chime with distilled or deionized water. Secure the can lid and place on paint shaker in an inverted position for 10 – 15 minutes. **DO NOT SHAKE LONGER THAN 15 MINUTES. Primer is now ready for use.**

### Application Equipment

Conventional, Air, Air Assisted Airless, HVLP, Electrostatic spray equipment may be used to apply this material. For your application, please contact the equipment manufacturer for more specific information on Conventional, HVLP or Electrostatic spray applications, and recommendations on hose diameter and lengths.

### Packaging, Yields, Shipping Weight

This material is available in the follow kit sizes:

Kit size	Approx. Yield (Mixed)	Approx. Shipping Weight
GK	3 gallons	13.25 lbs (6.0 kg)
QK	3 quarts	3.65 lbs (1.7 kg)
1QK	1 quart	1.70 lbs (0.77 kg)

Additional kit sizes are available upon request.

### Equipment Cleanup

Water will clean approximately 95% of liquid primer remaining on equipment. Follow with Deft's IS-248 Cleaning Solvent for Water Reducible Primer to remove any residual primer from equipment. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment

### Safety

Refer to the product label or Material Safety Data Sheet (MSDS) for each component for Personal Protective Equipment and Proper Handling.